ATRIUM PRODUCT DATA SHEET



Available Sizes
592x592x10mm
600x300x8.5mm

Samples Service

Technical Helpline
Email: samples@johnson-tiles.com
Fax: +44 (0)1782 577 379
Tel: +44 (0)1782 524 043

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

D Recycled content	00 00 2070
Range	Atrium
Category	Concrete, Floor Tiles,
	36+ Tiles
Collection	Select Collection
Short Code	ATRM4G
Colour	Graphite
Finish	Grip
Wall Suitability	Internal & External
Floor Suitability	Internal & External
Wet Barefoot	Yes
Material	Glazed Porcelain
Classificiation	Bla
Light Reflectance Value	18.00
CSV	٧3
PTV (4S)	Wet 36+ Dry 36+
PTV (TRL)	Wet 36+
R Value	11
Wet Ramp	-
PEI	IV
Traffic	Commercial

Up to 20%

 \varnothing Recycled Content

Physical Properties Test / Standard Requirement Test Result Length/Width ±0.6%≤ ± 2mm ±0.4% EN ISO 10545-2 Thickness ±5%≤ ± 0.5mm ±5% EN ISO 10545-2 Straightness of Sides ±0.5% ≤ ± 1.5mm ±0.4% EN ISO 10545-2 Rectangularity _____+ $\pm 0.5\% \leq \pm 2mm$ ±0.3% EN ISO 10545-2 Surface Flatness ±0.5% ≤ ± 2mm ±0.15% $\uparrow \uparrow$ EN ISO 10545-2 Water Absorption \bigcirc ≤0.5% ≤**0**.1% EN ISO 10545-3 **Modulus of Rupture** ≥35N/mm² ≥35N/mm² EN ISO 10545-4 Thermal Shock Pass Pass EN ISO 10545-9 Frost Resistance 潫 Resistant Resistant EN ISO 10545-12 Æ **Chemical Resistance** Min Class B Class A EN ISO 10545-13 Stain Resistance Min Class 3 Class 5 EN ISO 10545-14 Fire Rating Class A I FL Non ß N/A Not Applicable Combustible Weight/m² kg Thickness: 8.5mm 19kg Thickness: 10mm 22kg

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 364 represents a low slip potential. All rights reserved. No. 15600452.0 2024 Johnson Tiles. All rights reserved. JOHNSON TILES

