BLAKE PRODUCT DATA SHEET



Available Sizes

330x330x7.2mm 200x200x6mm 600x300x7.8mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) | 782 524 | | | | Fax: +44 (0) | 782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

${m arrho}$ Recycled Content	Up to 10%	
Range	Blake	
Category	Stone, Floor Tiles, PTV 36+	
	Tiles	
Collection	Select Collection	
Short Code	BLK01G	
Colour	lvory	
Finish	Grip	
Wall Suitability	Internal & External	
Floor Suitability	Internal & External	
Wet Barefoot	Yes	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	54.00	
CSV	V4	
PTV (4S)	Wet 36+ Dry 36+	
PTV (TRL)	Wet 36+	
R Value	11	
Wet Ramp	С	
PEI	IV	
Traffic	Commercial	

Physical Properties			
Test	Standard	Requirement	Test Result
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass
→	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass
-]+	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass
	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
$\begin{array}{ c c }\hline \downarrow \\\hline \uparrow \uparrow \\\hline \end{array}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
	Water Absorption EN ISO 10545-3	≤0.5%	Pass
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	Pass
	Thermal Shock EN ISO 10545-9	Pass	Pass
※	Frost Resistance EN ISO 10545-12	Resistant	Resistant
	Chemical Resistance EN ISO 10545-13	Min Class B	Pass
	Stain Resistance EN ISO 10545-14	Min Class 3	Pass
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible
kg	Weight/m ² Thickness:6mm Thickness:7.2mm Thickness:7.8mm Thickness:8.3mm		12.3kg 15.8kg 17.25kg 16.89kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, inadequate cleaning and maintenance will lead to a significant reduction the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potentia, 25 - 35 signifies a moderate slip potential and 364 represents a low slip potential. All figures are accurate at the time of this data sheets creation (19/16/20/4). Deposed Tiles in instead the required Strategy Tunstall Strategy Total Strategy Total Strategy.

