BUCKINGHAM PRODUCT DATA SHEET



Buckingham Range Marble Category Collection Absolute Collection Short Code BUC4DB Colour Anthracite Finish Soft Bush Hammered -Ductile Internal Only Wall Suitability Floor Suitability -Wet Barefoot -Material Ceramic Classificiation BIII Light Reflectance Value 15.00 V2 CSV

Up to 30%

 \mathcal{O} Recycled Content

Physical Properties			
Test / Standard		Requirement	Test Result
${\longleftrightarrow}$	Length/Width EN ISO 10545-2	±0.5%≤ ± 2mm	Pass
$\rightarrow \parallel \rightarrow$	Thickness EN ISO 10545-2	±10%≤±0.5mm	Pass
	Straightness of Sides EN ISO 10545-2	±0.3% ≤ ± 1.5mm	Pass
	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
$\stackrel{\mathbf{h}}{[]}$	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass
	Water Absorption EN ISO 10545-3	10% to 20%	Pass
	Modulus of Rupture EN ISO 10545-4	Ave I 5N/mm ²	≥25N/mm²
The second secon	Thermal Shock EN ISO 10545-9	Pass	Pass
*	Frost Resistance Not Applicable	N/A	Not suitable
ð	Chemical Resistance EN ISO 10545-13	Min Class B	Class A
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 5
	Fire Rating		Class Al Non Combustible
kg	Weight/m ² Thickness 6mm		10.68kg

Available Sizes 2700x900x6mm 1200x600x6mm

Samples Service

Tel: +44 (0)1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0)1782 524 111 Fax: +44 (0) 1782 577 379 Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential. 25 - 35 significas at moderate slip potentia and 36r represents a low slip potential. All rightres are accurate at the time of this data sheets creation (19/05/2024). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 SJZ, Registed in Englan No. 15600432. 6 2024 Johnson Tiles. All rights reserved.

