COAST PRODUCT DATA SHEET





Available Sizes

600x300x10.5mm 1190x600x10.5mm 890x890x10.5mm 600x600x10.5mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Ø Recycled Content	Up to 10%	
Range	Coast	
Category	Stone, Speckle, Floor Tiles,	
	PTV 36+ Tiles	
Collection	Select Collection	
Short Code	CST02B	
Colour	Beige	
Finish	Bush Hammered	
Wall Suitability	Internal & External	
Floor Suitability	Internal & External	
Wet Barefoot	Yes	
Material	Un-glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	53.00	
CSV	V4	
PTV (4S)	Wet 36+ Dry 36+	
PTV (TRL)	Wet 36+	
R Value	12	
Wet Ramp	С	
PEI	-	
Traffic	Commercial	

Physical Properties			
Test / Standard	Requirement	Test Result	
Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	±0.3%	
Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	±3%	
Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	±0.3%	
Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%	
Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%	
Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%	
Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥45N/mm²	
Thermal Shock EN ISO 10545-9	Pass	Pass	
Frost Resistance EN ISO 10545-12	Resistant	Resistant	
Chemical Resistance EN ISO 10545-13	Min Class B	Class A	
Stain Resistance EN ISO 10545-14		Class 5	
UV Colour Resistance		Unaffected by light	
Fire Rating Not Applicable	N/A	Class A I FL Non Combustible	
kg Weight/m² Thickness: 10.5mm		24.35kg	

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a light slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (19/05/2024). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registed in England No. 156/0437 @ 2024 Alphason Tiles All rights reserved.

