CONGLOMERATES PRODUCT DATA SHEET





Available Sizes

1200x1200x10.5mm 600x600x10.5mm 1200x600x10.5mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

 ${\bf Email: samples@johnson-tiles.com}$

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

Recycled Content	Up to 50%	
Range	Conglomerates	
Category	Stone, Speckle, Floor Tiles,	
	PTV 36+ Tiles	
Collection	Absolute Collection	
Short Code	CON05G	
Colour	Dark Grey	
Finish	Grip	
Wall Suitability	Internal & External	
Floor Suitability	Internal & External	
Wet Barefoot	Yes	
Material	Un-glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	15.00	
CSV	V2	
PTV (4S)	Wet 36+ Dry 36+	
PTV (TRL)	Wet 36+	
R Value	П	
Wet Ramp	С	
PEI	-	
Traffic	Commercial	

Physical Properties				
Test / Standard		Requirement	Test Result	
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	Pass	
<u></u>	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	Pass	
	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	Pass	
	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
\downarrow	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	Pass	
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%	
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥45N/mm²	
	Thermal Shock EN ISO 10545-9	Pass	Pass	
*	Frost Resistance EN ISO 10545-12	Resistant	Resistant	
	Chemical Resistance EN ISO 10545-13	Min Class B	Class A	
	Stain Resistance EN ISO 10545-14	Min Class 3	Class 5	
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible	
kg =	Weight/m² Thickness: 10.5mm		25kg	

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, hadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potentia, 25 - 35 signifies a moderate slip potentia and 364 represents a low slip notativity. All figures are accurate at the time of this data servers are accurated in Foral servers.

