## **COUNTRY RUSTIC** PRODUCT DATA SHEET



Collection **Minton Hollins Collection** Short Code CRFIA Colour White Finish **Gloss - Rustic Structure** Wall Suitability Internal Only Floor Suitability -Wet Barefoot -Material Glazed Ceramic Classificiation BIII CSV ٧I

Up to 20%

**Country Rustic** 

 $\mathcal{O}$  Recycled Content

Range Category

Physical Properties			
Test	/ Standard	Requirement	Test Result
	Length/Width EN ISO 10545-4	±0.5%≤ ± 2mm	±0.25%
+	<b>Straightness of Sides</b> EN ISO 10545-2	±0.3% ≤ ± 1.5mm	± 0.15%
-	<b>Rectangularity</b> EN ISO 10545-2	±0.5% ≤ ± 2mm	± 0.4%
$\stackrel{\mathbf{h}}{=} \uparrow \uparrow$	<b>Surface Flatness</b> EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.2%
$\overset{\uparrow}{=}$	<b>Warpage</b> EN ISO 10545-2	±0.5%≤ ± 2mm	0.30%
	Water Absorption EN ISO 10545-3	10% to 20%	15% to 17%
	<b>Modulus of Rupture</b> EN ISO 10545-4	Ave 15N/mm <sup>2</sup>	25N/mm²
*	Frost Resistance Not Applicable	N/A	Not suitable
Ä	<b>Chemical Resistance</b> EN ISO 10545-13	Min Class B	Class A-B (better)
	<b>Stain Resistance</b> EN ISO 10545-14	Min Class 3	Class 3 (better)
X	Crazing Resistance EN ISO 10545-11	Pass	Pass
	UV Colour Resistance		Unaffected by light
0	Scratch Hardness BS6431:Part13/EN101	≥3	4

B

Fire Rating

## Samples Service

**Available Sizes** 150x150x9.5mm

100x100x9.5mm

Tel: +44 (0)1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

**Technical Helpline** 

Tel: +44 (0)1782 524 111 Fax: +44 (0) 1782 577 379 Email: techadvice@johnson-tiles.com

## Class A1 Non Combustible

## www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential. 25 - 35 significas at moderate slip potentia and 36r represents a low slip potential. All rightres are accurate at the time of this data sheets creation (19/05/2024). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 SJZ, Registed in Englan No. 15600432. 6 2024 Johnson Tiles. All rights reserved.



