


COUNTRY STONES PRODUCT DATA SHEET



Available Sizes

100x100x6.5mm

Samples Service

Tel: +44 (0)1782 524 043

Fax: +44 (0)1782 577 379

Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0)1782 524 111

Fax: +44 (0)1782 577 379















Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

 Recycled Content **Up to 10%**

Range	Country Stones
Category	Stone
Collection	Intro Collection
Short Code	COS07A
Colour	Midnight
Finish	Satin
Wall Suitability	Internal Only
Floor Suitability	-
Wet Barefoot	-
Material	Glazed Vitrified
Classification	B11a
Light Reflectance Value	8.00
CSV	V2

Physical Properties

Test / Standard	Requirement	Test Result
 Length/Width EN ISO 10545-2	$\pm 0.6\% \leq \pm 2\text{mm}$	Pass
 Thickness EN ISO 10545-2	$\pm 5\% \leq \pm 0.5\text{mm}$	Pass
 Straightness of Sides EN ISO 10545-2	$\pm 0.5\% \leq \pm 1.5\text{mm}$	Pass
 Rectangularity EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	Pass
 Surface Flatness EN ISO 10545-2	$\pm 0.5\% \leq \pm 2\text{mm}$	Pass
 Water Absorption EN ISO 10545-3	3% to 6%	Pass
 Modulus of Rupture EN ISO 10545-4	$\geq 22\text{N/mm}^2$	Pass
 Thermal Shock EN ISO 10545-9	Pass	Pass
 Frost Resistance EN ISO 10545-12	Resistant	Not suitable
 Chemical Resistance EN ISO 10545-13	Min Class B	Pass
 Stain Resistance EN ISO 10545-14	Min Class 3	Pass
 UV Colour Resistance		Unaffected by light
 Fire Rating Not Applicable	N/A	Class A1 FL Non Combustible
 Weight/m² Thickness: 9.5mm		10.08kg

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (19/05/2024). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registered in England No. 15600432. © 2024 Johnson Tiles. All rights reserved.