DANUBE PRODUCT DATA SHEET





Available Sizes 592x592x10.5mm

Samples Service

Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379 Email: samples@johnson-tiles.com

Technical Helpline

Tel: +44 (0) 1782 524 111 Fax: +44 (0) 1782 577 379

Email: techadvice@johnson-tiles.com

www.johnson-tiles.com

	Up to 10%	
Range	Danube	
Category	Stone, Speckle, Floor Tiles	
Collection	Absolute Collection	
Short Code	DAN02L	
Colour	Beige	
Finish	Lapato	
Wall Suitability	Internal & External	
Floor Suitability	Internal Only	
Wet Barefoot	-	
Material	Glazed Porcelain	
Classificiation	Bla	
Light Reflectance Value	42.00	
CSV	V2	
PTV (4S)	Wet 0-24 Dry 36+	
PTV (TRL)	-	
R Value	-	
Wet Ramp	-	
PEI	IV	
Traffic	Commercial	

Physical Properties				
Test /	Standard	Requirement	Test Result	
	Length/Width EN ISO 10545-2	±0.6%≤ ± 2mm	±0.3%	
<u></u>	Thickness EN ISO 10545-2	±5%≤ ± 0.5mm	±3%	
- +	Straightness of Sides EN ISO 10545-2	±0.5% ≤ ± 1.5mm	±0.3%	
-	Rectangularity EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%	
$ \\ \boxed{ \\ \uparrow \uparrow } $	Surface Flatness EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%	
	Water Absorption EN ISO 10545-3	≤0.5%	≤0.1%	
	Modulus of Rupture EN ISO 10545-4	≥35N/mm²	≥35N/mm²	
	Thermal Shock EN ISO 10545-9	Pass	Pass	
	Frost Resistance EN ISO 10545-12	Resistant	Resistant	
	Chemical Resistance EN ISO 10545-13	Min Class B	Class A	
	Stain Resistance EN ISO 10545-14	Min Class 3	Pass	
	UV Colour Resistance		Unaffected by light	
	Fire Rating Not Applicable	N/A	Class A I FL Non Combustible	
kg	Weight/m² Thickness:9mm Thickness:10.5mm		21.78kg 27.32kg	

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36+ represents a low slip potential. All figures are accurate at the time of this data sheets creation (19/05/2024). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registed in Englar No. 156/0433 @ 2024 All plays are accurate.

