## **DANUBE** PRODUCT DATA SHEET



${\cal O}$ Recycled Content	Up to 10%
Range	Danube
Category	Stone, Speckle, Floor Tiles, PTV 36+ Tiles
Collection	Absolute Collection
Short Code	DAN03N
Colour	Grey
Finish	Natural
Wall Suitability	Internal & External
Floor Suitability	Internal Only
Wet Barefoot	-
Material	Glazed Porcelain
Classificiation	Bla
Light Reflectance Value	39.00
CSV	V2
PTV (4S)	Wet 36+ Dry 36+
PTV (TRL)	-
R Value	10
Wet Ramp	A
PEI	IV
Traffic	Commercial

Physical Properties			
Test / Standard	Requirement	Test Result	
Length/Width	±0.6%≤ ± 2mm	±0.3%	
EN ISO 10545-2			
↓ Thickness	±5%≤ ± 0.5mm	±3%	
↑ EN ISO 10545-2	13762 1 0.51111	2070	
Straightness of	\$ides ±0.5% ≤ ± 1.5mm	10.7%	
EN ISO 10545-2	±0.3% ≤ ± 1.5mm	±0.3%	
Rectangularity			
EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%	
↓ Surface Flatnes	s		
↑↑ EN ISO 10545-2	±0.5% ≤ ± 2mm	±0.3%	
Water Absorpti	on	-0.19/	
EN ISO 10545-3	≤0.5%	≤0.1%	
🐣 Modulus of Rup	ture ≥35N/mm²	≥35N/mm²	
EN ISO 10545-4	2551N/mm-	233N/mm*	
Thermal Shock	al Shock Pass	Pass	
EN ISO 10545-9	1 055	F 233	
💥 Frost Resistanc	e Resistant	Resistant	
EN ISO 10545-1	2 Resistant	Resistant	
Chemical Resist	ance Min Class B	Class A	
EN ISO 10545-1	3 Phill Class B	Class A	
Stain Resistance	e Min Class 3	Pass	
EN ISO 10545-1	4	F 235	
UV Colour Resis	stance	Unaffected by light	
Fire Rating	N/A	Class A I FL Non	
Not Applicable	170	Combustible	
kg Weight/m <sup>2</sup>			
Thickness:9mm		21.78kg	
Thickness:10.5m	ım	27.32kg	

## Samples Service Tel: +44 (0) 1782 524 043 Fax: +44 (0) 1782 577 379

Available Sizes

Email: samples@johnson-tiles.com

## Technical Helpline

Tel: +44 (0) | 782 524 | | | Fax: +44 (0) | 782 577 379 Email: techadvice@johnson-tiles.com

## www.johnson-tiles.com

Tile colours shown of the tile product on this data sheet are as accurate as the limitations of the printing process will allow. Due to the manufacturing process of all floor tiles there may be small variations in slip resistance. The slip resistance values provided are accurate at the time of testing and represent the standard production value. Please note, Inadequate cleaning and maintenance will lead to a significant reduction in the slip resistance of any tiles. The pendulum test results are displayed in line with The Health & Safety Executive guidelines whereby 0 - 24 represents a high slip potential, 25 - 35 signifies a moderate slip potential and 36r represents a low slip potential. All figures are accurate at the time of this data sheets creation (19/05/2024). Johnson Tiles Limited, Harewood Street, Tunstall, Stoke-on-Trent. ST6 5JZ. Registed in England No. 15600432. © 2024 Johnson Tiles. All rights reserved.



